



VERTICAL SCULPT MIX

SINGLE COMPONENT CEMENTICIOUS OVERLAY



VERTICAL SCULPT MIX PROVIDES AN AUTHENTIC LOOK AND FEEL OF BRICK, STONE, AND SLATE TO ANY STABLE INTERIOR OR EXTERIOR SURFACE. IT IS DESIGNED FOR EXCEPTIONAL ADHERENCE AND MANIPULATION TO ANY VERTICAL SURFACE.

PRODUCT HIGHLIGHTS

- One component mix. No extra additives. Just add water, mix and apply. Saves time and money.
- Ease of application.
- Vertical Sculpt Mix provides for a better overall performance than most resins, modifiers, and polymers.
- Vertical Sculpt Mix creates an authentic look of real brick, stone, and slate – at a fraction of the cost.
- Easily colored and manipulated to match any surroundings and landscape.
- Packaged in 40lb pail

USES

Vertical Sculpt Mix can be applied up to four inches thick to create the look of boulders, brick, limestone, sandstone, stacked stone, rock, and even wood.

QUICK LOOK:

Type : Single component cementacious overlay system
Toxicity: Low. Alkaline mixture. Harmful if swallowed.
VOC's: Zero
Flammability: Non-flammable
Composition: Portlant cement, sand and proprietary additives.
Odor: N/A
Coverage: 8-10sq.ft. at 1.5in thickness
**Coverage rates may vary depending on porosity, texture, application method and prior sealer application. Excess buildup should be avoided.*

Application Temperature:
Cured:

FOR MORE INFORMATION,
PLEASE SEE SDS.





VERTICAL SCULPT MIX

HOW TO USE:

An initial aggressive scratch coat of Bond Coat should be applied and allowed to dry before applying Vertical Stamp Mix. Temperature should be 40 degrees or above for a period of 48 hours.

To Mix 5 gallons: Place 8 to 9 quarts of clean, cool water in a separate bucket. Add a EZ-Color Pak, if desired, and mix for five minutes. Add half of the bucket of Vertical Sculpt Mix to the bucket of water and mix until product is evenly dispersed. Add the rest of the product and mix for three to five minutes. Let the product set up for five minutes and re-mix thoroughly. You may need to add small amounts of water to make the mix workable.

(Caution: Too much water can reduce the strength of concrete and in some cases cause cracking.)

The scratch coat should be wetted with EZChem Acrylo Bond immediately before applying Vertical Sculpt Mix. Apply Vertical Sculpt Mix to the scratch coat using a trowel. When a finger is able to press lightly into the product without removing material, a texture can be embossed into the surface.

PRECAUTIONARY STATEMENT:

Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Avoid breathing dust/fume/gas/mist/vapours/spray. Wash hands thoroughly after handling. Do not eat, drink or smoke when using this product. Wear protective gloves/protective clothing/eye protection/face protection. Take off contaminated clothing and wash before reuse. Store in a well-ventilated place. Keep container tightly closed. Store locked up. Dispose of contents/container to approved waste disposal site.

FIRST AID:

INHALATION: Move to fresh air to avoid nuisance symptoms.

SKIN CONTACT: Wash affected area thoroughly with soap and water. Rinse well. If irritation develops Get Medical Help.

EYE CONTACT: Rinse thoroughly with water for 15 minutes, lifting both eyelids. If irritation persists, Get Medical Help.

INGESTION: Rinse mouth with water. Drink 2 glasses of water to dilute. Do not induce vomiting. Get Immediate Medical Help. Never give anything by mouth to an unconscious person.

IN CASE OF FIRE:

This product is not flammable.

FOR EMERGENCY HELP

24 Hours a Day contact:

INFOTRAC at 1-800-535-5053