SINGLE COMPONENT

OVERLAY-UNIVERSAL WHITE OR GREY

Spray Bond Broom Texture

pray bond broom rexture

GREY UNIVERSAL MIX
Spray • Bond • Broom • Texture

SINGLE COMPONENT CEMENTITIOUS OVERLAY

THE UNIVERSAL OVERLAY MIX IS A SINGLE-COMPONENT OVERLAY SYSTEM THAT BONDS TO ALL CLEAN CONCRETE SURFACES TO PRODUCE A ROCK-HARD, WEATHERPROOF SURFACE.

COMES IN EITHER GREY OR WHITE 50 LB BAGS.

PRODUCT HIGHLIGHTS

- High bond, flexural and compressive strength. Consistant and evenly textured finish.
- Can be integrally colored with EZChem EZ Color Paks.
- Can be stained with EZChem Enviro Stain or Earthtone Stain for a wide array of decorative finishes.
- Can be sealed with EZChem Clear Acrylic Sealer or Colored Acrylic Sealer for a consistantly colored and durable surface.
- Packaged in 50lb bags
- Available in white and grey.

USES

Spray Mix sets to a rock hard surface that resists water penetration and provides a durable and beautiful textured surface. (*Coverage: Base Coat appx 175 sq.ft.*)

Texture Blend can be used in kitchens, bathrooms, patios, walkways, anywhere you need to produce adurable and decorative long lasting surface. (*Coverage:* 80sq.ft. per 40lb bag)

Bond coat provides a permanent bond when applied to properly prepared and cleaned concrete surfaces, typically used as a base. And should still be wet when the overlay mix(typically stamp mix) is applied over it. (**Coverage** 175-200 Sq. Ft. @ 1/16" per bag)

Broom, Sets to a rock-hard surface that resists water penetration and provides a durable and beautiful textured surface.(**Coverage**; Base coat = approx 125-175 g.ft Sq ft when applied no more that 1/4"

OUICKLOOK:

Type : Toxicity:

Toxicity: VOC's: Zero

Flammability: Non-flammable

Composition: Odor: N/A

Coverage: *Coverage rates may vary depending on porosity, texture, application method and prior sealer application. Excess buildup should be avoided.

Application Temperature: 50°-100°F

Cured: 28 days

FOR MORE INFORMATION,

PLEASE SEE SDS.









OVERLAY-UNIVERSAL

SURFACE PREPARATION:

The surface must be clean and free of any dirt or debris and properly prepared according to the Technical Data Sheet for UNIVERSAL OVERLAY. Just before applying UNIVERSAL OVERLAY the substrate must be primed with Bond It primer. **Do not** allow Bond It primer to dry completely MUST be wet for use.

HOW TO USE:

UNIVERSAL OVERLAY is typically applied to a damp surface. Remove any puddles and standing water (Saturated surface dry) before installation. Add 50 lb bag of UNIVERSAL OVERLAY to approximately 5.5 quarts (minimum 4.5 maximum 6.5) of water. Mix in a clean 5-gallon pail with a ½ mixer drill (Do not use a cement mixer)

Add EZChem EZ COLOR PAK (blend the Color Pak into the water first) if integral color is desired.

Add half the powdered material to the water, mix untill lump free, let sit for 5 minutes, then blend in the other half. Apply with a hopper gun, magic trowel (squeegee), steel pool trowel, brush, broom or roller

For a knockdown texture use 8-15 PSI through a relatively large orifice. As the wet, glossy material begins to dry to a matte or dull finish, it should be knocked down with a pool trowel or metal squeegee
For a bubble texture use 40 Psi through a relatively small orifice.

PRECAUTIONARY STATEMENT:

Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Avoid breathing dust/fume/gas/mist/vapours/spray. Wash hands thoroughly after handling. Do not eat, drink or smoke when using this product. Wear protective gloves/protective clothing/eye protection/face protection. Take off contaminated clothing and wash it before reuse. Store in a well-ventilated place. Keep container tightly closed. Store locked up. Dispose of contents/container to approved waste disposal site.

FIRST AID:

INHALATION: Move to fresh air to avoid nuisance symptoms.

SKIN CONTACT: Wash the affected area thoroughly with soap and water. Rinse well. If irritation develops Get Medical Help. EYE CONTACT: Rinse thoroughly with water for 15 minutes, lifting both eyelids. If irritation persists, Get Medical Help. INGESTION: Rinse mouth with water. Drink 2 glasses of water to dilute. Do not induce vomiting. Get Immediate Medical Help. Never give anything by mouth to an unconscious person.

IN CASE OF FIRE:

This product is not flammable.

TESTING DATA

Compressive Strength ASTM C-109 28 days 4000 PSI

Flexural Strength ASTM C-348 28 days 995

Tensile Strength ASTM C190 28 days 460 psi

Abrasion Resistance 28 day < 45%

FOR EMERGENCY HELP 24 Hours a Day contact: INFOTRAC at 1-800-535-5053

